

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C11D 17/00, 17/04, 7/06, 7/12, 7/14	A1	(11) International Publication Number: WO 95/18215 (43) International Publication Date: 6 July 1995 (06.07.95)
(21) International Application Number: PCT/US94/14807 (22) International Filing Date: 20 December 1994 (20.12.94) (30) Priority Data: 08/175,627 30 December 1993 (30.12.93) US (71) Applicant: ECOLAB INC. [US/US]; Ecolab Center, St. Paul, MN 55102 (US). (72) Inventors: HEILE, Bernard, Joseph; 6063 Lower 134th Street West, Apple Valley, MN 55124 (US). TARARA, James, John; 8976 St. Croix Road, Woodbury, MN 55125 (US). (74) Agent: DAIGNAULT, Ronald, A.; Merchant, Gould, Smith, Edell, Welter & Schmidt, 1000 Norwest Center, 55 East Fifth Street, St. Paul, MN 55101 (US).		(81) Designated States: AM, AT, AU, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, EE, ES, FI, GB, GE, HU, JP, KE, KG, KP, KR, KZ, LK, LR, LT, LU, LV, MD, MG, MN, MW, NL, NO, NZ, PL, PT, RO, RU, SD, SE, SI, SK, TJ, TT, UA, UZ, VN, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG), ARIPO patent (KE, MW, SD, SZ). Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: STABLE HYGROSCOPIC DETERGENT ARTICLE (57) Abstract The invention provides an environmentally stable detergent article. Normally, hygroscopic caustic detergent materials can be made resistant to absorption of ambient humidity or water by introducing a barrier coating onto the caustic detergent. The barrier also renders the highly active alkaline material safe for human handling. The coated detergent article can further be enclosed in a film enclosure or wrapping which provides further protection for handling during production, shipment, storage and final end use. The coated article can be removed from any packaging material, inserted into a water spray-on dispenser and used to create a concentrated aqueous detergent for use in ware washing machines. In order to obtain control over dispensing, hydrophobic coatings can be nicked, split, peeled or partially removed using other means to provide an initial surface of caustic detergent exposed to the water spray. The water spray can then dispense the detergent and either melt or dissolve the hydrophobic coating in a controlled manner.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

STABLE HYGROSCOPIC DETERGENT ARTICLE

Field of the Invention

The invention is directed to stabilized hygroscopic
5 solid block alkaline detergent material that can be used
in a variety of cleaning regimens including
institutional and industrial ware washing, laundry, hard
surface cleaning, etc. The caustic detergent comprises
typically a source of alkalinity, a hardness
10 sequestering agent and other active ingredients useful
in the washing regimen. The detergent articles of the
invention are stabilized to the absorption of water from
the environment and are suitable for handling by human
operators of washing equipment. The invention also
15 relates to methods of using the stabilized hygroscopic
detergent in a cleaning regimen.

Background of the Invention

The development of solid block cleaning
20 compositions has revolutionized the manner in which
detergent compositions are dispensed by commercial and
institutional ware washing, laundry, hard surface
cleaning equipment. Such equipment routinely use large
quantities of cleaning materials by inserting large
25 block detergent articles into dispensers which convert
the solid detergent into a concentrate using a water
spray. The concentrate is directed to a use locus,
typically a ware washing machine, laundry washing
machine, etc. Solid block compositions offer the unique
30 advantages over other forms of detergents including
improved handling, enhance safety, elimination of
component segregation during transportation, storage and
use and increase concentrations of active ingredients
within the composition.

35 Because of the benefits, the solid cleaning
compositions such as those disclosed in Fernholz, U.S.
Reissue Patent Nos. 32,763 and 32,818 have quickly
replaced conventional forms of ware washing detergents
in commercial and institutional markets. In large part,

commercial solid cast materials are packaged in disposable thermoplastic bottles or capsules. The highly alkaline materials are dispensed from the plastic capsule using a water spray within a dispenser apparatus. When the alkaline detergent is consumed during ware washing operations, the plastic capsule remains for disposal or recycling. Other alkaline materials are packaged in disposable or soluble wrapping material such as Gladfelter, U.S. Patent Nos. 5,198,198 and 5,234,615 and as shown in Gladfelter U.S. Serial No. 07/699,688. In this packaging alternative, a soluble detergent cake or soluble pellets are introduced into a water soluble wrapping or film enclosure. The article is then inserted directly into a spray on dispenser wherein the entire package and contents are dispensed into a use locus. No detergent or any soluble wrapping remains in the dispenser once consumed.

Colgate Palmolive United Kingdom Patent No. 1,031,831 teaches a non-caustic organic surfactant based detergent tablet having a colored coating of a water soluble polymer. The detergent tablet contains a water soluble organic detergent such as an alkyl benzene sulfonate, higher fatty alcohol sulfates, etc. coated with a water soluble coating made from film forming ingredients such as a film forming synthetic organic polymer that will dissolve readily in water such as polyvinyl alcohol, ethoxylated polyvinyl alcohol, sodium carboxy methyl cellulose, hydroxy propyl methyl cellulose, hydroxy ethyl cellulose and polyvinyl pyrrolidone. Based on the disclosure of the Colgate Palmolive patent, the patent is primarily directed to a single use household laundry tablet. Such a tablet contains less than about 200 grams total of typically household laundry detergent materials. Biard et al., U.S. Patent No. 4,219,435, teach alkaline detergent tablets for ware washing and typical laundry detergent tablets that are enclosed in an inorganic hydrated salt

coating. The coating comprises a hydrated salt having a melting point of 30°-90°C including sodium acetate, sodium metaborate, sodium orthophosphate, sodium potassium tartrate, potassium aluminum sulfate and other such hydrates. Gromer et al., U.S. Patent No. 4,219,436, teach a high density, high alkalinity, single unit dose dish washing detergent tablet. Gromer et al teach that the automatic dish washing detergent tablet, configured for use in a household machine, contains as a source of alkalinity, an alkaline silicate material. Gromer et al. teach that the detergent tablets must be made in such a manner that the density of the tablet be greater than 1.4 grams per cubic centimeter in order to provide effective cleaning. Gromer et al. teach that the tablets are preferably surfactant free. However, if surfactant is used, Gromer et al. teach that the surfactant be sprayed onto carrier particles or onto some portion of the active ingredients prior to tableting. Gromer et al. do not teach the use of organic materials as a stabilizing coating.

Alkaline detergent articles comprising some substantial proportion of an alkali metal hydroxide or other compositions with similar alkalinity are substantially hygroscopic. If left unprotected from atmospheric humidity, the materials when exposed to the ambient atmosphere absorb substantial quantities of water at a rate substantially greater than about 20 grams of water per 100 grams of alkaline detergent material per day (conditions: 100°F and 65% rel. humidity). The absorption of such quantities of water rapidly renders the cast article unsuitable for use in most dispensing apparatus. The water softens the article to a degree that it cannot be easily handled and swells to a degree that it no longer can be easily inserted into dispensers. After an initial rapid absorption, the water absorption rate is reduced as the water saturates the surface and prevents continued rapid

absorption. The alkaline detergent article contains sufficient alkalinity to be substantially corrosive to the user and to other surfaces common in the work place. The absorbance of significant amounts of water increase the corrosivity of the material and also increases the chances that users or services common in the use locus can be contaminated with a corrosive material. Additionally, the absorbed water can affect the physical stability and dimensional stability of the cast product. The cast products are sized with dimensions that ensure the cast block can be readily inserted into a spray on dispenser and can be used to regularly dispense or control the amount of detergent. Such a cast material requires physical stability, i.e. the material remains a solid block having substantial surface hardness and does not, in an important sense, change from a solid into a liquid paste or gel form. Further, the dimensions of the cast block should remain substantially constant and be sized appropriately for easy insertion into a dispenser. Accordingly, a substantial need exists for developing a moisture resistant multi-use detergent article. The resistant article prevents absorption of environmental humidity into the cast detergent material. The coated cast detergent article preferably absorbs less than about 2 grams water per 100 grams of material per day when exposed to the ambient atmosphere. Further, the article preferably provides enhanced safety during use. Contact between the user or sensitive surfaces is prevented in the use locus to the highly alkaline materials in the detergent article.

Brief Discussion of the Invention

The invention relates to an alkaline detergent article comprising a solid block detergent mass having a barrier coating. The barrier coating provides safety and stability to the detergent mass. The detergent mass is rendered safe for handling by personnel involved in

inserting the detergent article into a water spray detergent dispenser. Further, the barrier provides a stability benefit in that the alkaline mass does not absorb substantial quantities of water, substantially
5 reducing the utility of the detergent mass in washing operations. The detergent article coating stabilizes the detergent mass such that the detergent mass does not absorb more than 2, preferably less than 5 grams of
10 water per 100 grams of detergent mass per day at the conditions discussed above. When viewed on a 30 day basis, the coated detergent article should not absorb more than 5 grams of water per 100 grams of detergent. At room temperature (70-75°F) and about 50% relative
15 humidity, the coated detergent mass gains little or no water, preferably gains between 0.3 and 5 grams of water per 100 grams of detergent on a 30 day basis. Using more severe conditions of 100°F and 65% relative
20 humidity, the detergent mass preferably gains from 0.8 to 4 grams of water per 100 grams of detergent on a 30 day basis when coated with the coatings of the invention.

The detergent article comprising a coating on a detergent mass can optionally be packaged in a film envelope. The film can be a flexible sheet like
25 material that is insoluble in aqueous materials, including alkaline and acidic aqueous solutions. Further, the film envelope can comprise polymeric materials that are insoluble in any aqueous material or soluble only in aqueous alkaline systems or only in
30 aqueous acidic systems.

Another aspect of the invention relates to hydrophobic coatings on the detergent mass in a detergent article that require an initial step in
35 introducing a passage for water or other dispensing stream through the coating prior to insertion of the detergent article in the dispenser. Some hydrophobic coatings are substantially water resistant and can

resist the effects of the dispensing stream for a significant period of time before the coating is melted, dissolved or worn away by the water stream. To ensure the dispensing of adequate proportions of the detergent mass in the presence of a newly installed detergent article, the detergent coating can be breached, cut, or partially removed in such a way that access is provided for the water stream into the detergent mass as it is inserted into the dispenser.

10 The detergent article of the invention is typically manufactured by blending the detergent ingredients in a moldable, plastic or liquid form shaping the liquid into a detergent mass having a desired shape for ease of insertion into a dispenser, coating the mass with a preferred coating composition and optionally packaging the detergent article in a film envelope. In use the film envelope, if used, is opened, the detergent article removed from the envelope and inserted into a dispenser. The coating on the detergent article can be compromised to ensure that the initial contact between the article and the dispensing spray dissolve at least some portion of the detergent creating a concentrate for use in the use locus.

For the purposes of this application, the term "detergent mass" relates to a bulk solid mass of alkaline detergent typically greater than about 100 grams, typically 2 Kg to 5 Kg, to that can be inserted into a dispenser that uses a spray directed onto a surface of the detergent mass hence the detergent as an aqueous concentrate to a washing locus. The term "detergent article" connotes the detergent mass having a barrier coating.

Detailed Description of the Invention

35 The invention provides a detergent article comprising a detergent mass having an integral coating substantially covering the detergent mass to the degree

that the detergent mass absorbs environmental water at a rate such that the detergent can be handled and dispensed in spray on type dispensers. The detergent article can optionally be packaged in a flexible film envelope provide additional protection to the detergent article.

The detergent article of the invention can be made having a detergent mass comprising a variety of solid cleaning compositions. The detergent mass can be used to form concentrates comprising detergent compositions, sanitizing compositions, conveyor lubricants, floor cleaners and the like. The cleaning compositions of the invention typically comprise conventional active ingredients that can be blended to obtain the properties required in the type of composition being manufactured. Typical ingredients used in the detergent mass of this invention includes a variety of ingredients as discussed below.

20 Alkaline Sources

The cleaning composition produced according to the invention may include effective amounts of one or more alkaline sources to enhance cleaning of a substrate and improve soil removal performance of the composition. The composition can comprise about 0.1-70 wt-% of an alkaline source, preferably about 10-50 wt-%.

Suitable alkali metal hydroxides include, for example, sodium or potassium hydroxide. An alkali metal hydroxide may be added to the composition in the form of solid beads dissolved in an aqueous solution, or a combination thereof. Alkali metal hydroxides are commercially available as a solid in the form of prilled beads having a mix of particle sizes ranging from about 12-100 U.S. mesh, or as an aqueous solution, as for example, as a 50 wt-% and a 73 wt-% solution. It is preferred that the alkali metal hydroxide is added in the form of an aqueous solution, preferably a 50 wt-%

hydroxide solution, to reduce the amount of heat generated in the composition due to hydration of the solid alkali material.

A cleaning composition may comprise another
5 alkaline source other than an alkali metal hydroxide. Examples of useful secondary alkaline sources include a metal silicate such as sodium or potassium silicate or metasilicate, a metal carbonate such as sodium or
10 potassium carbonate, bicarbonate, sesquicarbonate, and the like; a metal borate such as sodium or potassium borate, and the like; ethanolamines and amines; and other like alkaline sources. Such alkalinity agents are commonly available in either aqueous or powdered form, either of which is useful in formulating the present
15 cleaning compositions. The amount of water in the detergent mass can be important. Excess water can promote the decomposition of the coating or the film envelope. Water content of the detergent mass should be maintained between 5 to 30 wt.-%, Preferable 10 to 15
20 wt.-%.

Secondary Hardening Agents/Solubility Modifiers

The present compositions include an effective amount of a secondary hardening agent, as for example,
25 an amide such stearic monoethanol amide or lauric diethanol amide, or an alkylamide, and the like; a solid polyethylene glycol or a propylene glycol, and the like; starches that have been made water soluble through an acid or alkaline treatment process; various inorganics
30 that impart solidifying properties to a heated composition upon cooling, and the like. Such compounds may also vary the solubility of the composition in an aqueous medium during use such that the cleaning agent and/or other active ingredients may be dispensed from
35 the solid composition over an extended period of time. The composition may include a secondary hardening agent in an amount of about 5-20 wt.-%, preferably about 10-15

wt-%.

Detergent Fillers

A cleaning composition may include a minor but effective amount of one or more of a detergent filler which does not perform as a cleaning agent per se, but cooperates with the cleaning agent to enhance the overall cleaning capacity of the composition. Examples of fillers suitable for use in the present cleaning compositions include sodium sulfate, sodium chloride, starch, sugars, C₁-C₁₀ alkylene glycols such as propylene glycol, and the like. Preferably, a detergent filler is included in an amount of about 1-20 wt-%, preferably about 3-15 wt-%.

15

Defoaming Agents

A minor but effective amount of a defoaming agent for reducing the stability of foam may also be included in the present urea-based cleaning compositions. Preferably, the cleaning composition includes about 0.0001-5 wt-% of a defoaming agent, preferably about 0.01-1 wt-%.

Examples of defoaming agents suitable for use in the present compositions include silicone compounds such as silica dispersed in polydimethylsiloxane, fatty amides, hydrocarbon waxes, fatty acids, fatty esters, fatty alcohols, fatty acid soaps, ethoxylates, mineral oils, polyethylene glycol esters, alkyl phosphate esters such as monostearyl phosphate, and the like. A discussion of defoaming agents may be found, for example in U.S. Patent No. 3,048,548 to Martin et al., U.S. Patent No. 3,334,147 to Brunelle et al., and U.S. patent No. 3,442,242 to Rue et al., the disclosures of which are incorporated by reference herein.

35

Anti-redeposition Agents

A cleaning composition may also include an anti-

red deposition agent capable of facilitating sustained suspension of soils in a cleaning solution and preventing the removed soils from being redeposited onto the substrate being cleaned. Examples of suitable anti-redeposition agents include fatty acid amides, fluorocarbon surfactants, complex phosphate esters, styrene maleic anhydride copolymers, and cellulosic derivatives such as hydroxyethyl cellulose, hydroxypropyl cellulose, and the like. A cleaning composition may include about 0.5-10 wt-%, preferably about 1-5 wt-%, of an anti-redeposition agent.

Dyes/Odorants

Various dyes, odorants including perfumes, and other aesthetic enhancing agents may also be included in the composition. Dyes may be included to alter the appearance of the composition, as for example, Direct Blue 86 (Miles), Fastusol Blue (Mobay Chemical Corp.), Acid Orange 7 (American Cyanamid), Basic Violet 10 (Sandoz), Acid Yellow 23 (GAF), Acid Yellow 17 (Sigma Chemical), Sap Green' (Keyston Analine and Chemical), Metanil Yellow (Keystone Analine and Chemical), Acid Blue 9 (Hilton Davis), Sandolan Blue/Acid Blue 182 (Sandoz, Hisol Fast Red (Capitol Color and Chemical), Fluorescein (Capitol Color and Chemical), Acid Green (Ciba-Geigy), and the like.

Fragrances or perfumes that may be included in the compositions include, for example, terpenoids such as citronellol, aldehydes such as amyl cinnamaldehyde, a jasmine such as C1S-jasmine or jasmal, vanillin, and the like.

Chelating/sequestering Agents

The composition may include a chelating/sequestering agent such as an aminocarboxylic acid, a condensed phosphate, a phosphonate, a polyacrylate, and the like. In general, a chelating

agent is a molecule capable of coordinating (i.e., binding) the metal ions commonly found in natural water to prevent the metal ions from interfering with the action of the other deterative ingredients of a cleaning composition. The chelating/sequestering agent may also function as a threshold agent when included in an effective amount. Preferably, a cleaning composition includes about 0.1-70 wt-%, preferably from about 5-50 wt-%, of a chelating/sequestering agent.

Useful aminocarboxylic acids include, for example, N-hydroxyethyliminodiacetic acid, nitrilotriacetic acid (NTA), ethylenediaminetetraacetic acid (EDTA), N-hydroxyethyl-ethylenediaminetriacetic acid (HEDTA), diethylenetriaminepentaacetic acid (DTPA), and the like.

Examples of condensed phosphates useful in the present composition include sodium and potassium orthophosphate, sodium and potassium pyrophosphate, sodium tripolyphosphate, sodium hexametaphosphate, and the like. A condensed phosphate may also assist, to a limited extent, in solidification of the composition by fixing the free water present in the composition as water of hydration.

The composition may include a phosphonate such as aminotris(methylene phosphonic acid), hydroxyethylidene diphosphonic acid, ethylenediaminetetrae(methylene phosphonic acid), diethylenetriaminepente(methylene phosphonic acid), and the like. It is preferred to use a neutralized or alkaline phosphonate, or to combine the phosphonate with an alkali source prior to being added into the mixture such that there is little or no heat generated by a neutralization reaction when the phosphate is added.

Polyacrylates suitable for use as cleaning agents include, for example, polyacrylic acid, polymethacrylic acid, acrylic acid-methacrylic acid copolymers, hydrolyzed polyacrylamide, hydrolyzed polymethacrylamide, hydrolyzed polyamide-methacrylamide

copolymers, hydrolyzed polyacrylonitrile, hydrolyzed polymethacrylonitrile, hydrolyzed acrylonitrile-methacrylonitrile copolymers, and the like. For a further discussion of chelating agents/sequestrants, see
5 Kirk-Othmer, Encyclopedia of Chemical Technology, Third Edition, volume 5, pages 339-366 and volume 23, pages 319-320, the disclosure of which is incorporated by reference herein.

10 Cleaning Agents

The composition comprises at least one cleaning agent which is preferably a surfactant or surfactant system. A variety of surfactants can be used in a cleaning composition, including anionic, cationic,
15 nonionic and zwitterionic surfactants, which are commercially available from a number of sources. For a discussion of surfactants, see Kirk-Othmer, Encyclopedia of Chemical Technology, Third Edition, volume 8, pages 900-912. Preferably, the cleaning composition comprises
20 a cleaning agent in an amount effective to provide a desired level of cleaning, preferably about 30-95 wt-%, more preferably about 50-85 wt-%.

Anionic surfactants useful in the present urea-based cleaning compositions, include, for example,
25 carboxylates such as alkylcarboxylates and polyalkoxycarboxylates, alcohol ethoxylate carboxylates, nonylphenol ethoxylate carboxylates, and the like; sulfonates such as alkylsulfonates, alkylbenzenesulfonates, alkylarylsulfonates, sulfonated
30 fatty acid esters, and the like; sulfates such as sulfated alcohols, sulfated alcohol ethoxylates, sulfated alkylphenols, alkylsulfates, sulfosuccinates, alkylether sulfates, and the like; and phosphate esters such as alkylphosphate esters, and the like. Preferred
35 anionics are sodium alkylarylsulfonate, alpha-olefinsulfonate, and fatty alcohol sulfates.

Nonionic surfactants useful in cleaning

compositions, include those having a polyalkylene oxide polymer as a portion of the surfactant molecule. Such nonionic surfactants include, for example, chlorine-, benzyl-, methyl-, ethyl-, propyl-, butyl- and other like alkyl-capped polyethylene glycol ethers of fatty alcohols (Dehypon LT 104; Henkel); polyalkylene oxide free nonionics such as alkyl polyglycosides (Glucopon 225; Henkel); amine oxides; sorbitan and sucrose esters and their ethoxylates; alkoxyated ethylene diamine; alcohol alkoxyates such as alcohol ethoxylate propoxylates, alcohol propoxylate ethoxylate propoxylates, alcohol ethoxylate butoxylates, and the like; nonylphenol ethoxylate, polyoxyethylene glycol ethers of C₁₂-C₁₅ fatty alcohol such as Ceteareth-27 (Plurofac A-38, BASF-Wyandotte) or Pareth 25-7 (Neodol 25-7, Shell), and the like; carboxylic acid esters such as glycerol esters, polyoxyethylene esters, ethoxylated and glycol esters of fatty acids, and the like; carboxylic amides such as ethanolamine condensates, monoalkanol amine condensates, polyoxyethylene fatty acid amides, and the like; and polyalkylene oxide block copolymers including an ethylene oxide/propylene oxide block copolymer such as those commercially available under the trademark PLURONIC 25R8 (BASF-Wyandotte), and the like; and other like nonionic compounds.

Cationic surfactants useful for inclusion in a cleaning composition for sanitizing or fabric softening, include amines such as primary, secondary and tertiary monoamines with C₁₈ alkyl or alkenyl chains, amine oxides, ethoxylated alkylamines, alkoxyates of ethylenediamine, imidazoles such as a 1-(2-hydroxyethyl)-2-imidazoline, a 2-alkyl-1-(2-hydroxyethyl)-2-imidazoline, and the like; and quaternary ammonium salts, as for example, alkylquaternary ammonium chloride surfactants such as n-alkyl(C₁₂-C₁₈)dimethylbenzyl ammonium chloride, n-tetradecyldimethylbenzylammonium chloride monohydrate, a

naphthylene-substituted quaternary ammonium chloride such as dimethyl-1-naphthylmethyllummonium chloride, and the like; and other like cationic surfactants.

Also useful are zwitterionic surfactants such as β -
5 N-alkylaminopropionic acids, N-alkyl- β -iminodipropionic acids, imidazoline carboxylates, N-alkylbetaines, sultaines, and the like.

Other Additives

10 Urea-based compositions made according to the invention may further include conventional additives such as a chelating/sequestering agent, bleaching agent, alkaline source, secondary hardening agent or solubility modifier, detergent filler, defoamer, anti-redeposition
15 agent, a threshold agent or system, aesthetic enhancing agent (i.e., dye, perfume), and the like. Adjuvants and other additive ingredients will vary according to the type of composition being manufactured.

20 Bleaching Agents

Bleaching agents for use in cleaning compositions for lightening or whitening a substrate, include bleaching compounds capable of liberating an active halogen species, such as -Cl, -Br, -OCl and/or -OBr,
25 under conditions typically encountered during the cleansing process. Suitable bleaching agents for use in the present cleaning compositions include, for example, chlorine-containing compounds such as a chlorine, a hypochlorite, chloramine. Preferred halogen-releasing
30 compounds include the alkali metal dichloroisocyanurates, chlorinated trisodium phosphate, the alkali metal hypochlorides, monochloramine and dichloramine, and the like. Encapsulated chlorine sources may also be used to enhance the stability of the
35 chlorine source in the composition (see, for example, U.S. Patent No. 4,618,914, the disclosure of which is incorporated by reference herein). A bleaching agent

may also be a peroxygen or active oxygen source such as hydrogen peroxide, perborates, sodium carbonate peroxyhydrate, phosphate peroxyhydrates, potassium permonosulfate, and sodium perborate mono and

- 5 tetrahydrate, with and without activators such as tetraacetylene diamine, and the like. A cleaning composition may include a minor but effective amount of a bleaching agent, preferably about 0.1-10 wt-%, preferably about 1-6 wt-%.

10

Coatings

- Coatings used in manufacturing the detergent articles of the invention comprise both soluble and insoluble organic materials that can form an integral
15 coating on the detergent mass. The integral coating substantially covers the surface of the detergent mass preventing the absorption of environmental water from the atmosphere into the surface of the detergent mass. Further, the coating prevents contact between operators
20 of ware washing equipment from contact with the highly alkaline caustic nature of the material.

- The coating comprises a continuous layer covering substantially the entire detergent mass having a thickness of about 0.1 to 12 millimeters, preferably
25 about 0.5 to 3 millimeters. Preferably as little as possible of the coating materials is used to provide an adequate barrier. Consequently, the detergent article comprises about 0.3 to 50 wt-%; preferably 1 to 10 wt-%, most preferably about 1 to 5 wt-% based on the total
30 weight of the coated detergent article. Maintaining the integrity of the water excluding coating is important to maintain stability of the detergent mass. The detergent mass should be cast with surface imperfections that extend from the surface of the detergent mass to a
35 degree that the imperfections do not breach the coating after formation. The coating must form an adequate seal covering all surface distortions.

Coatings that can be used to manufacture the detergent article of the invention are those coatings which are chemically stable to the chemical constituents of the detergent mass. Both water soluble and water insoluble coatings can be used. The coatings can be introduced onto the detergent mass using any conventional coating technique such as coextrusion, spray coating, curtain coating, immersion, surface molding and others. Combinations of coating processes can also be used to ensure that a complete coating is formed. For example, an initial coating can be coextruded surrounding an extruded detergent mass core. Such a process would leave open uncoated ends on the detergent mass. Such an article can be further coated using spraying, curtain coating, etc. to seal the ends.

Coating compositions can comprise materials that are applied in the form of liquids. Such liquids can be room temperature solids that can be applied in the form of a heated melt or in the form of a solvent based solution or dispersion. Such dispersions can be made using water as a liquid base or using other solvents such as ethanol, methanol, propanol, petroleum ether, benzene toluene, etc. Preferably solvent based materials are applied in the form of aqueous dispersions for reasons of cost and safety. Dispersion materials useful for manufacturing the detergent articles of the invention comprise dispersions that can be sprayed or otherwise coated on the detergent mass of the invention leaving a coating after the aqueous or other vehicle has evaporated. Such dispersions preferably comprise 10-80 wt-% solids, the balance being water stabilizers and other functional ingredients. The dispersion should have a viscosity that permits ease of coating but should maintain sufficient solids to rapidly coat the detergent mass. Suitable dispersions for use in the coatings of the composition include poly(ethylene-co-vinylacetate),

poly(ethylene-co-acrylic acid), poly(ethylene-co-methylacrylate), acrylic homopolymers such as polyacrylic acid, polymethacrylic acid, polymethylmethacrylate, styrene-butadiene-styrene
5 copolymers, styrene-acrylic copolymers.

The coatings can also be applied in the form of an aqueous solution of materials. Soluble materials can include soluble polymeric materials such as soluble surfactants, soluble cellulosic materials, soluble
10 salts, etc. Examples of such materials include polyethylene glycol (polyethylene oxide), polyethylene oxide, polypropylene oxide, block copolymers, polyacrylic acid, etc.

The coatings of the invention can also be applied
15 in the form of a melt material. Such materials are commonly substantially organic compositions having a melting point greater than about 30°C, preferably about 35-55°C, have a melt viscosity that can obtain a continuous, uniform coating at about 30-60°C, can
20 provide a substantial mass in the coating on the detergent mass of the invention to obtain moisture barrier properties and are stable to the presence of the alkaline materials in the detergent mass. Among the useful coatings include waxy materials. Such waxes
25 include low molecular weight (e.g. 1000-6000 molecular weight) polyethylenes having a softening point of about 66 to about 150°C and petroleum waxes such as paraffin wax having a melting point of from about 60 to about 100°C, microcrystalline wax having a melting point from
30 about 60 to about 100°C. Synthetic waxes made by polymerizing carbon monoxide and hydrogen such as Fisher-Tropsch wax. Further, hydrogenated animal or vegetable fats or oils can also be used if possessing the appropriate melting points and melt viscosity. Such
35 oils include lard, hydrogenated soy bean oil, hydrogenated cotton seed oil, and hydrogenated castor oil. Further, hydrogenated fatty acids obtained from

the oils discussed above can also be used as coating materials. Further derivatives of the fatty acids set forth above can be used as coating materials. Preferred fatty acid derivatives include fatty acid amides made by
5 reacting the fatty acid with nitrogen bases. Preferred nitrogen bases include ammonia and an amine. Preferred amines include methyl amine, dimethyl amine, ethyl amine, diethyl amine, monoethanol amine, diethanol amine, and other reactive amines providing at least one active
10 hydrogen on the amine nitrogen for reaction with the fatty acid carboxylic acid group. Preferred coating materials for use in a melt coating composition of the invention include hydrogenated and non-hydrogenated coco fatty acid, hydrogenated and non-hydrogenated stearic
15 acid, hydrogenated and non-hydrogenated stearic acid monoethanol amide, hydrogenated and non-hydrogenated stearic acid diethanol amide, paraffin wax, polyethylene glycol having a molecular weight ranging from about 1000 to 10,000, pluronic block copolymers comprising at least
20 one polyethylene oxide block and at least one polypropylene oxide block having molecular weights of about 1000 to 10,000.

The coating compositions formed on the detergent mass can comprise a single layer comprising the organic
25 material. Further, the coating can comprise a single layer of organic material with inorganic materials used as diluents or as materials that can promote the solubility or other removal of the coating. Such organic coatings can contain as an inorganic component,
30 sodium chloride, sodium sulfate, sodium carbonate, sodium acetate, sodium metasilicate, sodium phosphate, trisodium phosphate, trisodium polyphosphate, sodium acrylic polymers and others. The organic coatings that optionally can contain some proportion of inorganic
35 material can also be used with other coating layers. The organic coating can be formed over a wholly inorganic coating comprising materials discussed above

or can be used with a separate distinct organic coating as discussed above.

Film Enclosure

5 Once coated the detergent article of the invention can be packaged in a separate film envelope. The envelope can be water soluble or water insoluble. Water soluble envelopes disclosing the detergent article of the invention can be manufactured from a number of water
10 soluble films which are available commercially. Suitable water soluble film forming materials included, but are not limited to polyvinyl alcohol, polyvinyl acetate, methyl cellulose, hydroxyethyl cellulose, carboxymethyl cellulose, carboxymethyl hydroxyethyl
15 cellulose, polyvinyl pyrrolidone, polyalkyloxazoline and film forming derivatives of polyethylene glycol. Polyvinyl alcohol which is preferred as a water soluble film is an excellent film forming material, has good strength and pliability under most operating conditions.
20 Commercially available polyvinyl alcohol compositions for casting as films vary in molecular weight and degree of hydrolysis for most film applications, molecular weights in the range of about 10,000 to about 100,000 are preferred. Hydrolysis is the percent by which
25 acetate groups of the precursor polyvinyl acetate has been removed leaving hydroxyl groups on a polyvinyl alcohol material. For film applications the range of hydrolysis typically is about 70 to about 99.9+%. The term polyvinyl alcohol always includes some residual
30 acetate material remaining on the polyvinyl alcohol backbone. Since water soluble films and water soluble bags are manufactured from a number of sources including monosol films from Chris Kraft Industries. Suitable water insoluble film forming materials include, but are
35 not limited to polyethylene, polypropylene, polyvinyl chloride, polyvinylidene dichloride, polyethylene terephthalate, polyethylene-co-acrylic acid, polyimide,

nylon and other structural materials. Such water insoluble envelopes need to be physically removed prior to insertion of the detergent article into a dispenser, such films can be removed simply by tearing the film at
5 any appropriate location on the film surface. However, the film envelopes can be manufactured containing means to promote film envelope removal. Materials useful in the film envelope used in packaging the detergent article should be capable of forming an in tact envelope
10 surrounding the detergent article, should have a minimum tensile strength at break of about 5000-10,000 psi, should have a minimum tear resistance of about 75-100 g/mil, should have a thickness from about 1 to 15 mil, preferably about 1.5 to 7 mil.

15 The detergent mass can take any appropriate shape suitable for coating and for final packaging in the film envelope if used. We have found that preferred shapes for use in the detergent article can comprise shapes having large internal volumes with minimal external
20 surface area. Accordingly, preferred shapes include generally spherical masses, cylindrical masses, generally square masses, etc. Such shapes reduce the amount of coating required to prevent moisture from contaminating the surface of the detergent mass.
25 Further, these shapes can be manufactured with minimal surface imperfections that can render the surface coating ineffective for protecting the surface of the detergent mass.

The following examples provide a basis for
30 understanding certain embodiments of the invention and contain a best mode. All parts are parts by weight.

Example 1

Coating

An organic coating composition was made by
35 introducing into a heated glass beaker about 98.82 parts of a stearic acid diethanol amide, 0.08 part of a dye and 1 part by weight of an EO/PO defoamer polymer

composition. The mixture was heated until melted, stirred until uniform and was set aside to coat an alkaline detergent mass.

Example 2

5 Into a heated beaker is placed a polyethylene glycol (ethylene oxide homopolymer) having a molecular weight of about 8000 and trisodium phosphate hydrate (12 moles of water). The weight ratio of the material was about 3:1 polymer to phosphate. The contents were
10 heated and mixed until uniform. The contents were then removed from heat and maintained for coating experiments.

Example 3

Using the procedure of Examples 1 or 2, a coating
15 material was made comprising approximately a 1:1 weight ratio of a non-ionic surfactant material comprising a polyoxypropylene, polyoxyethylene, polyoxypropylene block copolymer having on the average 18 moles of propylene oxide, 163 moles of ethylene oxide and 18
20 moles of propylene oxide (PLURONIC 25R8 - BASF-Wyandotte) and stearic acid.

Example 4

Solid Alkaline Detergent

Into a stirred beaker equipped with a heating
25 element was placed 15.984 parts by weight of a 50 wt-% active aqueous sodium hydroxide solution, 0.5 part by weight of a sodium chlorite (NaClO_3) solution, 3.133 parts by weight of hard water, 0.5 part of nonionic surfactants, 4 parts by weight of a 50 wt-% active
30 solution of polyacrylic acid and the mixture was stirred until uniform. Into the stirred mixture was then added 38.484 parts of bead sodium hydroxide, 6.496 parts of dense ash (Na_2CO_3) and a 30.9 parts by weight of sodium tripolyphosphate coated with nonionic surfactant. The
35 mixture was stirred until uniform and cast into a number of four pound spheres using a plastic container/mold.

Example 5

The cast solid sphere of Example 4 was coated with the coating of Example 1 by dipping the sphere into a heated container enclosing a melt of the coating material of Example 1. The coating formed on this sphere in a continuous uniform layer and comprised approximately 4 wt-% of the cast material.

Example 6

Example 5 was repeated with the coating composition of Example 2.

Example 7

Example 5 was repeated except with the coating composition of Example 3.

Example 8

The method of Example 6 was repeated except that the melt coating composition comprised a poly ethylene glycol (polyethylene oxide homopolymer) having a molecular weight of 8000 in place of the blended coating composition.

Example 9

The coated alkaline detergent product of Example 8 was further coated by spraying onto the coated detergent block an aqueous solution comprising approximately 55 parts by weight of soft water and approximately 45 parts by weight of trisodium phosphate hydrate (12 moles water).

Example 10

A sphere of Example 4 was coated with a polyacrylic acid homopolymer having an average molecular weight of about 4500. The coating on the spherical cast solid was formed by spraying onto the cast solid an approximately 50 wt-% active aqueous solution of the polyacrylic acid homopolymer until a uniform coating was formed.

Stability

The stability testing consists of monitoring the weight gain and visual changes that occur to the samples. The samples are tested using three storage

conditions. The storage conditions consist of 100°F-65%RH, Cycle 100°F-65%RH, and room temperature (72°F-50%RH).

5 The following data table displays the sample disposition, sample ID, coating weight percent, and percent weight gained per time. The data table also shows the average coating weight percent and percent weight gained per time. The data reveals that the samples are gaining weight slowly but stability is
10 excellent.

STEARIC ACID AMIDE SOLID ON CAUSTIC SOLID % WEIGHT GAIN

5	Sample Disposition	Sample ID	Coating Wt-%	4 Days	24 Days	43 Days
10	RT 72°F 50%	43F	7.79%	0.06%	0.22%	0.42%
	RT 72°F 50%	43G	8.84%	0.08%	0.24%	0.43%
	RT 72°F 50%	43M	10.89%	0.10%	0.32%	0.56%
	RT 72°F 50%	43N	11.74%	0.10%	0.28%	0.50%
	DISP 100°F 65%	43A	12.13%	-	-	-
15	DISP 100°F 65%	43B	7.90%	-	-	-
	DISP 100°F 65%	43H	8.58%	-	-	-
	DISP 100°F 65%	43K	11.82%	-	-	-
	DISP 100°F 65%	43L	11.76%	-	-	-
	DISP 100°F 65%	43O	11.33%	-	-	-
20	DISP 100°F 65%	43P	9.06%	-	-	-
	DISP 100°F 65%	43R	10.95%	-	-	-
	CYCLE	43C	8.95%	0.17%	0.47%	0.55%
	CYCLE	43I	8.53%	0.20%	0.75%	0.94%
	CYCLE	43U	8.67%	0.17%	0.53%	0.65%
25	CYCLE	43Y	9.95%	0.21%	0.72%	0.87%
	100°F/ 65% RH	43D	7.98%	0.22%	0.54%	0.75%
	100°F/ 65% RH	43E	9.12%	0.21%	0.50%	0.67%
	100°F/ 65% RH	43J	11.67%	0.25%	0.64%	0.88%
	100°F/ 65% RH	43Q	11.23%	0.28%	0.69%	0.96%
30	100°F/ 65% RH	43S	11.23%	0.28%	0.65%	0.87%
	100°F/ 65% RH	43T	9.54%	0.24%	0.59%	0.79%
	100°F/ 65% RH	43V	10.91%	0.30%	0.83%	1.18%
	100°F/ 65% RH	43W	10.51%	0.29%	0.81%	1.12%
	100°F/ 65% RH	43X	10.63%	0.33%	0.89%	1.27%
35	100°F/ 65% RH	43Z	13.54%	0.33%	0.84%	1.16%
	100°F/ 65% RH	AVG	10.27%	0.27%	0.70%	0.96%
	CYCLE	AVG	9.03%	0.19%	0.62%	0.76%
	RT	AVG	9.81%	0.09%	0.26%	0.48%

Performance

The dispensing performance The spot and film performance test consisted of evaluating the two solid barrier coatings on a caustic solid detergent article and a standard SOLID POWER[®] brand detergent. The test evaluated redeposition and milk glasses for spotting and filming after 20 cycles in a Hobart C-44. The test conditions were city water (4.5 grains), 1500 ppm of beef stew soil, and 1000 ppm of hot point soil.

Dispensing

The dispensing test consisted of evaluating the two suppliers and comparing them with standard Solid Power. The equipment used was a modified Solitron 1000/1500 dispenser. The dispensing conditions consisted of; City water, 5.6-90° spray nozzle operating at 20 psig.

The modifications consisted of a sleeve (7 in OD and 5.25 in ID) that fits inside the dispenser. The sleeve adapts the current 7 in diameter dispenser to a 5.25 in diameter dispenser. The sleeve rests on a grate (6.25 in OD and 2 in ID). The grate is flat and shaped like a doughnut. The grate supports the product and the sleeve. The inner hole allows the water to spray on the product without any interference.

The Solid Power standard product starts at its initial weight and dispensing rate decreases with increasing time (cycles). The Solid on Solid product (labeled W or RP) exhibits a dispensing delay before the coating dissolves. This occurrence is much more evident at 115°F. The Solid on Solid samples dispense exactly like standard Solid Power once part of the coating dissolves. The amount of delay time at 115°F is 20 min and 30 sec at 145°F.

A high temperature is needed to reduce the delay time. If this condition is met, no problems should occur with delay times.

26

SUMMARY OF RESULTSSOLID ON SOLID

	TEST	CONDITIONS	Pwr BALL <u>Witco</u>	Pwr BALL <u>RP</u>	SOLID <u>POWER</u>
5	_____	_____			
	Dispensing				
	Charge Time				
	(min)	115°F	39.0	20.5	0.0
10	20 psi, 5.6/90				
	nozzle	145°F	1.0	30 (sec.)	0.1
	Total Time				
	(min)	115°F	137.5	175.0	37.5
15	20 psi, 5.6/90				
	nozzle	145°F	17.5	22.0	17.5
	20 Cycle Spot & Film				
20	Milk, Spot				
	(Film)	1000 ppm	4(2.33)	4(2.33)	5(2.5)
		2000 ppm	1(2.67)	1(2.5)	1(2.17)
25	Redep, Spot				
	(Film)	1000 ppm	2(2.17)	1(2.33)	3(2.5)
		2999 ppm	1(2.33)	1(2.5)	1(2.33)
	Surface Tension				
30	(dynes/cm)				
		0 ppm		73.0	73.0
		1 ppm		57.0	73.0
		25 ppm		36.7	73.0
35					

The data is shown in table form. The data shows that at 1000 ppm (0.1%) all of the products had the same film rating, but the solid on solid samples had reduced the spotting. This result is understandable considering
5 that Stearamide diethanol amide coating material is a surfactant. The 2000 ppm (0.2%) milk glasses showed similar results on spot and film for all products.

The data shows again that at 1000 ppm the solid on solid reduces the spotting. The 2000 ppm samples all
10 gave the same results.

The significance of the performance testing tells us that solid on solid does not have any detrimental effects on product performance such as spotting or surface tension. In fact, at lower concentrations it
15 can reduce spotting.

The detergent mass of the invention can be manufactured by casting a liquid melt or a liquid dispersion, compacting powder into a solid, compacting pellets into a solid, or using any other manufacturing
20 scheme that would result in a detergent mass having mechanical stability and a minimum mass of about 100 grams. Representative examples of patents teaching such manufacturing methods include Fernholz et al., U.S. Reissue Nos. 32,763 and 32,818, Heile et al., U.S.
25 Patent Nos. 4,680,134 and 4,595,520. The most common method for manufacturing the cast solid detergent mass of the invention involves slurrying the desired ingredients in an aqueous medium at a concentration such that a hydrated alkaline salt is formed having a melting
30 point of less than about 50°C. If the materials are manufactured at a temperature greater than 50°C, the combined materials will freeze when cooled. Alternatively, the materials can be slurried using anhydrous materials that when hydrate, solidify into the
35 detergent mass.

One additional method for forming the cast solid detergent articles of the invention involves using

extrusion technology wherein the materials of the detergent are suspended in an aqueous medium which is mixed and extruded in the form of a cylindrical extrudate which can rapidly harden to form the detergent mass. These manufacturing methods are disclosed in copending U.S. Serial Nos. _____, _____, and _____. However, any manufacturing technique that can form a stable detergent mass having greater than about 100 grams can be used.

10 Preferred coatings used on the detergent mass to form an alkaline detergent article comprise substantially water resistant materials that can form a continuous coating formed on the exterior of the detergent mass separating the detergent mass from
15 contact with the user and from contact with the environment.

Even though several characteristics and advantages of the invention have been set forth in the foregoing description, together with the details of the structure
20 and function of the invention, the disclosure is illustrative only, and changes may be made in detail, especially in matters of shape, size and arrangement of parts, within principles of the invention, to the full extent indicated by the broad, general meaning of the
25 appended claims.

WE CLAIM:

1. A solid detergent article, stabilized to the effects of heat and humidity in the ambient environment,
5 said article comprising a barrier layer coating and a detergent mass comprising at least 100 grams of an alkaline hygroscopic detergent comprising a major proportion of a source of alkalinity selected from an alkali metal hydroxide, an alkali metal carbonate, an
10 alkali metal silicate or mixtures thereof, said mass substantially uniformly coated with said barrier layer coating that protects the mass from the absorption of greater than about 5 grams of water per 100 grams of detergent per 30 days; said barrier layer coating also
15 permits safe handling of the detergent mass during use.

2. The article of claim 1 wherein the detergent mass comprises about 1 to 75 wt-% of a source of alkalinity, about 1 to 40 wt-% of an organic or
20 inorganic sequestrant composition; and about 1 to 30 wt-% of water of hydration.

3. The article of claim 1 wherein the detergent mass comprises about 0.5 to 5 kilograms.

25

4. The article of claim 1 wherein the barrier layer coating comprises an organic layer having a melting point greater than about 30°C.

30 5. The composition of claim 4 wherein the organic layer comprises a fatty acid amide.

6. The composition of claim 5 wherein the fatty acid amide is made from an monoalkanol amine or a
35 dialkanol amine and a C₆₋₂₀ fatty acid.

7. The composition of claim 4 wherein the barrier

layer coating comprises a polyethylene oxide homopolymer having a melting point greater than about 30°C and a solubility less than about 70 grams per 100 grams of water at 30°C.

5

8. The composition of claim 4 wherein the barrier layer coating comprises a block copolymer comprising at least one block of ethylene oxide and at least one block of propylene oxide having a melting point greater than about 30°C.

10

9. The article of claim 1 wherein the barrier layer coating comprises a hydrophobic inorganic hydrated salt.

15

10. The article of claim 1 wherein the barrier layer coating comprises a substantially organic layer having distributed therein about 1 to 50 wt-% of an inorganic hydrated salt.

20

11. The article of claim 1 wherein a layer of a hydrophobic hydrated inorganic salt is placed over the detergent mass and the barrier layer coating.

25

12. A packaged coated detergent article comprising:

- (a) the detergent article of claim 1 and
- (b) a film envelope enclosing the article.

30

13. The article of claim 12 wherein the film envelope is insoluble in an aqueous medium.

14. The article of claim 12 wherein the film envelope comprises a polyolefin, a polyvinyl chloride, a polyvinylidene dichloride, or a polyester.

35

15. The article of claim 12 wherein the film

envelope is soluble in an alkaline aqueous medium.

16. The article of claim 12 wherein the film envelope comprises a poly[ethylene-co-acrylic] composition.

17. A method of dispensing an alkaline solid detergent article comprising:

(a) exposing a portion of the surface of an alkaline detergent mass comprising a major proportion of a source of alkalinity selected from an alkali metal hydroxide, an alkali metal carbonate, an alkali metal silicate or mixtures thereof, said detergent mass substantially uniformly coated with a barrier layer that protects the mass from the absorption of greater than about 5 grams of water per 100 grams of detergent per 30 days to form a dispensable detergent article; and

(b) inserting the dispensable detergent article into a dispenser comprising a water spray positioned such that the spray dispenses the exposed detergent mass.

18. The method of claim 17 wherein prior to exposing a surface of the detergent mass, a film is removed from the detergent article.

19. The method of claim 18 wherein the film is a water insoluble polymeric film selected from the group consisting of a polyolefin film, a polyvinylidene chloride film, a polyvinyl chloride film or a polyester film.

20. A solid detergent article, stabilized to the effects of heat and humidity in the ambient environment, said article comprising at least 100 grams of a caustic hygroscopic detergent mass comprising a major proportion

of an alkali metal hydroxide, a water softening amount of a hardness sequestering agent, and an effective amount of water of hydration to render the detergent mass a solid, said mass substantially uniformly coated
5 with a substantially organic barrier layer that protects the mass from the absorption of greater than about 5 grams of water per 100 grams of detergent per 30 days, said coating also permits safe handling of the detergent mass during use, said coating comprising an organic
10 coating material having a melting point of greater than 30°C.

21. The article of claim 20 wherein the detergent mass comprises about 1 to 75 wt-% of sodium hydroxide,
15 about 1 to 40 wt-% of sodium tripolyphosphate and about 1 to 30 wt-% of water of hydration.

22. The article of claim 21 wherein the barrier layer comprises a fatty acid amide.
20

23. The composition of claim 22 wherein the fatty acid amide is made from a monoalkanol amine or a dialkanol amine and a C₆₋₂₀ fatty acid.

24. The composition of claim 20 wherein the barrier layer coating comprises a polyethylene oxide polymer having a melting point greater than about 30°C and a solubility less than about 70 grams of polymer per 100 grams of water at 30°C.
30

25. The composition of claim 21 wherein the barrier layer coating comprises a block copolymer comprising at least one block of ethylene oxide and at least one block of propylene oxide having a melting
35 point greater than about 30°C.

26. A method of dispensing a detergent article

comprising inserting the detergent article of claim 1, packaged in a film envelope soluble in water or in an alkaline aqueous solution, into a spray on dispenser, and spraying onto the film envelope and detergent

5 article an aqueous stream that can dissolve and remove the film, the barrier layer coating and at least some portion of the detergent mass to create an alkaline detergent concentrate for use in a washing locus.

10 27. The method of claim 26 wherein the film comprises a polyvinyl alcohol.

28. The method of claim 26 wherein the film comprises a poly(ethylene-coacrylic acid).

15

29. The method of claim 26 wherein the film comprises a poly(ethylene-covinyl alcohol).

30. A method of manufacturing a detergent article
20 stabilized to the effects of heat and humidity in the ambient environment, said article comprising at least 100 grams of an alkaline hygroscopic detergent mass comprising a major proportion of a source of alkalinity selected from an alkali metal hydroxide, an alkali metal
25 carbonate, an alkali metal silicate or mixtures thereof, said method comprising extruding a thickened liquid detergent mass from an extruder in the form of an extrudate having a diameter of 2 to 8 inches forming the extrudate into a cylindrical mass having a height of 2
30 to 8 inches permitting the extrudate to solidify, coating the extrudate with a barrier coating layer that protects the mass from the absorption of greater than about 5 grams of water per 100 grams of detergent for 30
35 days, said coating also permitting safe handling of the detergent mass during use; and packaging the detergent mass in a film envelope.

31. The method of claim 30 wherein the detergent mass comprises about 1 to 75 wt-% of an alkali metal hydroxide, about 1-40 wt-% of an organic or inorganic sequestrant composition; and about 1-30 wt-% of water of
5 hydration.

32. The method of claim 30 wherein the barrier coating layer comprises an organic layer having a melting point of greater than about 30°C.
10

33. The method of claim 30 wherein the organic layer comprises a fatty acid amide.

34. The method of claim 30 wherein the fatty acid
15 amide is made from a monoalkanol amine or a dialkanol amine and a C₆₋₂₀ fatty acid.

35. The method of claim 30 wherein the film envelope comprises a polyolefin film, a polyvinyl
20 chloride film, a polyvinylidene dichloride film or a polyester film.

36. The method of claim 30 wherein the film is soluble in an aqueous medium.
25

37. The method of claim 30 wherein the film is soluble in an alkaline aqueous medium.

38. The method of claim 17 wherein the water used
30 in dispensing the detergent mass has a temperature of about 130-150°F.

39. The detergent article of claim 1 wherein the detergent mass comprises a cylinder having a height of
35 3-6 inches and a diameter of 4-8 inches.

40. The detergent article of claim 1 wherein the

35

detergent mass comprises a spherical mass having a diameter of 3-7 inches.

5

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 94/14807

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 C11D17/00 C11D17/04 C11D7/06 C11D7/12 C11D7/14

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 6 C11D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP,A,0 002 293 (THE PROCTER & GAMBLE CO.) 13 June 1979 see the whole document ---	1,9
A	US,E,32 818 (FERNHOLZ ET AL.) 3 January 1989 cited in the application see the whole document ---	1,3,12, 17,20,26
A	WO,A,92 01037 (ECOLAB INC.) 23 January 1992 see the whole document ---	1,4,12, 20
A	GB,A,1 031 831 (COLGATE-PALMOLIVE CO.) 2 June 1966 cited in the application see the whole document ---	1,4,30, 32
	--- -/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "B" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

15 May 1995

Date of mailing of the international search report

23.05.95

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Serbetsoglou, A

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 94/14807

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	GB,A,989 683 (COLGATE-PALMOLIVE CO.) 22 April 1965 see the whole document ---	1,4,30, 32
A	WO,A,93 01266 (WINBRO GROUP LTD.) 21 January 1993 see the whole document ---	1,12,17, 26
A	EP,A,0 055 100 (JEYES GROUP LTD.) 30 June 1982 see page 6 - page 10 see page 15 - page 16; claims -----	1,5,6

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 94/14807

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A-2293	13-06-79	BE-T- 56 DE-A- 2857472 NL-T- 7815064 CA-A- 1109752 FR-A- 2443502 GB-A- 2041966 US-A- 4219435	18-04-80 17-07-80 30-05-80 29-09-81 04-07-80 17-09-80 26-08-80
US-E-32818	03-01-89	BE-A- 904138 CA-A- 1125621 EP-A, B 0003769 JP-C- 1229398 JP-A- 54152007 JP-B- 59004480 US-A- 4569781 US-A- 4569780 US-E- RE32763	15-05-86 15-06-82 05-09-79 19-09-84 29-11-79 30-01-84 11-02-86 11-02-86 11-10-88
WO-A-9201037	23-01-92	AU-B- 646063 AU-A- 8209191 CA-A- 2085985 EP-A- 0537256 JP-T- 6501276 US-A- 5384364	03-02-94 04-02-92 04-01-92 21-04-93 10-02-94 24-01-95
GB-A-1031831		BE-A- 631834 FR-A- 1363342	25-09-64
GB-A-989683		BE-A- 615884 CH-A- 424054 DE-B- 1223977 FR-A- 1327781 NL-A- 276598 US-A- 3231505 US-A- 3231506	04-09-63 25-01-66 25-01-66
WO-A-9301266	21-01-93	US-A- 5209864 AU-A- 2317692 BR-A- 9206236 EP-A- 0646166	11-05-93 11-02-93 27-12-94 05-04-95

INTERNATIONAL SEARCH REPORT

Inter-
mal Application No
PCT/US 94/14807

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO-A-9301266		US-A- 5366706	22-11-94
EP-A-0055100	30-06-82	AT-T- 9818	15-10-84
		AU-B- 540392	15-11-84
		AU-A- 7911081	15-07-82
		CA-A- 1182371	12-02-85
		GB-A, B 2089830	30-06-82
		US-A- 4460490	17-07-84

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.